

TRAY LINER AND PROTECTOR

Reliance® Dextex Trayliner
Wetlaid NW 72 gsm

Colors available:



STEAM

EO

FORM

IRRAD

Characteristics	Test Method	Unit	Typical Values
Average mass of 1m ²	ISO 536	g/m ²	72
pH-value	ISO 6588-2		5.9
Chloride	ISO 9197	%	0.027
Sulphate	ISO 9198	%	0.108
Optical Brightening increase	ISO 2470-2	%	No increase in brightness due to the optical brightener of more than 1% - Conform
Fluorescence	Visual Observation	-	number of spots ≤ 5 ; spots axis > 1mm / 0,01 m ² - Conform
Specific requirements for wetlaid non-woven			
Elongation	ISO 1924-2	%	6 in machine direction 12 in cross direction
Thickness	ISO 534	µm	240
Air Permeability	ISO 9237	l/m ² /s at 200 Pa	680
Tensile strength, dry	ISO 1924-2	kN/m	1.2 in machine direction 0.7 in cross direction
Tensile strength, wet	ISO 3781	kN/m	0.8 in machine direction 0.5 in cross direction
Tear resistance	ISO 1974	mN	1450 in machine direction 1550 in cross direction
Dry Bursting Strength	ISO 2758	kPa	150
Wet Bursting Strength	ISO 3689	kPa	110
Liquid absorptive capacity	ISO 9073-6	%	430

Last update: January 2018

STAY IN TOUCH:

✉ medical@ahlstrom-munksjo.com

EMEA

☎ +33 2 32 41 61 00

NORTH AMERICA

☎ 860-654-8300

ASIA - CHINA

☎ +86 212 330 7330

SOUTH AMERICA

☎ +55 193 878 9238